

CLAIMS

1. A resin composition comprising:
an alicyclic structure-containing polymer;
5 a hindered amine compound; and
a releasing agent,
wherein the releasing agent and the alicyclic
structure-containing polymer satisfy the following
relationship:
10 $10 \geq |s_1 - s_2| \geq 0.8 \text{ [(MPa)}^{0.5}\text{]},$
wherein s_1 represents a solubility parameter of the
releasing agent, and s_2 represents a solubility parameter
of the alicyclic structure-containing polymer.
- 15 2. The resin composition according to claim 1, wherein
the alicyclic structure-containing polymer is obtained by
hydrogenating an aromatic vinyl polymer in which a content
of an aromatic vinyl monomer unit is 50% by weight or more.
- 20 3. The resin composition according to claim 1 or 2,
wherein the ratio of the number of carbon-carbon double
bonds to the total number of carbon-carbon bonds in the
alicyclic structure-containing polymer is 0.15% or less.
- 25 4. The resin composition according to any one of claims 1
to 3, wherein the hindered amine compound has (1) a
molecular weight in the range of from 1,500 to 100,000, and
(2) a light transmittance of 90% or more at a wavelength of
400 nm as measured using a 5% by weight of chloroform
30 solution and a cell with an optical path of 10 mm.

5. The resin composition according to any one of claims 1 to 4, wherein the releasing agent is a fatty acid amide releasing agent.
- 5 6. The resin composition according to any one of claims 1 to 5, wherein the resin composition has a light transmittance of 88% or more at a wavelength of 400 nm and an optical path length of 3 mm.
- 10 7. A molded body obtained by molding the resin composition according to any one of claims 1 to 6.